

Property	Test Method	Standard Value
300% Modulus	ASTM D-412-75	4.2MPa
Ultimate Tensile	ASTM D-412-75	10.05MPa
Ultimate Elongation	ASTM D-412-75	600%
Tear strength	ASTM D-624C-73	28.3KN/m
Fungus Resistance	ASTM G-21	28 days exposure No growth
Moisture Absorption 7 days at 90°C in H <sub>2</sub> O		3.0% wt. Gain



ID as Supplied (Min)/mm	ID after Recovered (Max)/mm	Wall Thickness after Recovered (Nom)/mm	Application Range/mm	Length/mm (±10%)
EDL-CP1-20/12-0	Ø12	2.5	Ø13-Ø16	70
EDL-CP2-28/16-0	Ø16	2.5	Ø18-Ø24	70
EDL-CP3-47/23-0	Ø 23	2.6	Ø25-Ø28	70
EDL-CP4-80/46-0	Ø46	2.6	Ø48-Ø70	70

## Key Features

- Made of EPDM rubber
- Easy and fast installation/removal
- Can meet a variety of configuration requirements
- Provides sealing protection over multi-core cable ends
- Simple and fast installation, no tools required. Accommodating size ranges from 13mm to 70mm.
- Sealing tight, high rebound even after prolonged years of aging and exposure.
- Water-resistant.
- No mastic or tape required.
- No torches or heat required.
- Resists fungus, acids, alkalis, and ozone.
- No training required for installation.

**Property of Gamma Electronics Inc.**

2818 Metropolitan Place, Suite A, Pomona, CA 91767

[www.gammaelectronics.net](http://www.gammaelectronics.net)